

## DP10

### METAL-POLYMER ANTI-FRICTION PLAIN BEARINGS



### APPLICATIONS

**Automotive** – Braking systems, clutches, hinges – door, bonnet, boot, cabriolet roof tops, pedals, pumps – axial, piston, gear, vane, seat mechanisms, steering systems, struts and shock absorbers, wiper systems, etc.

**Industrial** – Agricultural equipment, compressors – scroll and reciprocating, construction equipment, food and beverage, material handling equipment, forming machines – metal, plastic and rubber, office equipment, medical and scientific equipment, packaging equipment, pneumatic and hydraulic cylinders, pumps and motors, railroad and tramways, textile machinery, valves, etc.

### CHARACTERISTICS

- Good wear and low friction performance over a wide range of loads, speeds and temperatures in dry running conditions
- Very good performance in lubricated applications particularly in marginally lubricated applications
- Suitable for linear, oscillating and rotating movements
- Lead-free material compliant to ELV, WEEE, and RoHS specifications

### AVAILABILITY

**Bearing forms made to order:** Standard forms in special dimensions, half-bearings, special shapes obtained by stamping or deep drawing, bearings with locating notches, lubricant holes and machined/stamped grooves, customized bearing designs



BEARING PROPERTIES		UNITS	VALUE
--------------------	--	-------	-------

**GENERAL**

Maximum load, p	Static	N/mm <sup>2</sup>	250
	Dynamic	N/mm <sup>2</sup>	140
Operating temperature	Min	°C	- 200
	Max	°C	280
Coefficient of linear thermal expansion	Parallel to the surface	10 <sup>-6</sup> /K	11
	Normal to the surface	10 <sup>-6</sup> /K	30

**DRY**

Maximum sliding speed, U	m/s	2.5
Maximum pU factor	N/mm <sup>2</sup> x m/s	1.0
Coefficient of friction, f		0.03 - 0.25*

**OIL LUBRICATED**

Maximum sliding speed, U	m/s	5.0
Maximum pU factor	N/mm <sup>2</sup> x m/s	10.0
Coefficient of friction, f		0.02 - 0.08

**RECOMMENDATIONS**

Shaft surface roughness, Ra	Dry	µm	0.3 - 0.5
	Lubricated	µm	≤ 0.05 - 0.40*
Shaft surface hardness	Unhardened acceptable, improved bearing life	HB	> 200

\* Depending on operating conditions

**OPERATING PERFORMANCE**

Dry	Good
Oil lubricated	Good
Grease lubricated	Fair
Water lubricated	Not recommended
Process fluid lubricated	Fair

**FOR SUPERIOR / LEAD-FREE PERFORMANCE**

Grease lubricated	DP4 / DX
Water lubricated	DP4-B
Process fluid lubricated	DP4 / DP31

**MICROSECTION**

