

EP®15

ENGINEERED FOR SUN



APPLICATIONS

Solar Power Equipment, Outdoor Applications, Recreational Applications

CHARACTERISTICS

- UV-resistant
- Abrasion-resistant
- Lightweight
- Low coefficient of friction
- Very good bushing performance in dry working conditions
- Good bushing performance in lubricated or marginally lubricated applications
- Corrosion-resistant in humid/saline environments
- Very good price performance ratio
- Very good weight performance ratio
- Within injection molding tool feasibility unlimited dimensions and design features
- Compliant to ELV, WEEE and RoHS specifications

AVAILABILITY

Bearing forms made to order: Cylindrical bushings, flanged bushings, thrust washers, sliding plates, half-bushings, customized bearing designs



POLYMER: POM (POLYOXYMETHYLENE)


ADDITIVES: PTFE (POLYTETRAFLUOROETHYLENE), UV STABILIZER

CHARACTERISTICS	STANDARD	VALUE	UNITS
Charpy unnotched impact strength	ISO 179/1eU	kJ/m ²	45
Charpy notched impact strength	ISO 179/1eA	kJ/m ²	4,5
Coefficient of linear thermal expansion	ISO 11359-2:1999-10	x10 ⁻⁶	120
Minimum temperature		°C / °F	- 40 / - 40
Maximum temperature		°C / °F	125 / 260
Maximum extended temperature limit		°C / °F	125 / 260
Density	DIN EN ISO 1183-1 :2013-04	g/cm ³	1,50
	DIN EN ISO 1183-2 :2004-10		
Tensile strength	DIN EN ISO 527-1 :2012-06	N/mm ² / psi	50 / 7252
	DIN EN ISO 527-2 :2012-06		
	DIN EN ISO 527-3 :2003-07		
Elastic modulus in tension	DIN EN ISO 178:2013-09	N/mm ² / psi	2750 / 398854
	DIN EN ISO 527-1:2012-06		
	DIN EN ISO 604:2003-12		
Maximum static load		N/mm ² / psi	65 / 9500
Coefficient of friction, f			0,09 - 0,15
Color			Blue

OPERATING PERFORMANCE

Dry	Very Good
Oil lubricated	Good
Grease lubricated	Good
Water lubricated	Fair
Process fluid lubricated	Good after resistance testing

MICROSECTION



POM + PTFE + UV Stabilizer

