

Multilube

THERMOPLASTIC PLAIN BEARINGS



APPLICATIONS

Industrial – Linkages, seat suspensions

CHARACTERISTICS

- Good bearing performance in dry working conditions.
- Good bearing performance in lubricated or marginally lubricated applications
- Corrosion resistant in humid/saline environments
- Good price performance ratio
- Very good weight performance ratio
- Within injection moulding tool feasibility unlimited dimensions and design features

AVAILABILITY

Bearing forms made to order: Cylindrical bushings, flanged bearings, thrust washers, sliding plates, half-bearings, customized bearing designs



BEARING PROPERTIES		UNITS	VALUE
--------------------	--	-------	-------

GENERAL

Maximum load, p	Static	N/mm ²	60
	Dynamic	N/mm ²	30
Operating temperature	Min	°C	- 40
	Max	°C	80
	Momentary	°C	120
Coefficient of linear thermal expansion		10 ⁻⁶ /K	101

DRY

Maximum sliding speed, U		m/s	1.5
Maximum pU factor		N/mm ² x m/s	0.6
Coefficient of friction, f			0.1 - 0.2

RECOMMENDATIONS

Shaft surface roughness, Ra		µm	0.2 - 0.8
Shaft surface hardness	Normal	HB	> 200
	For longer service life	HB	> 350

OPERATING PERFORMANCE

Dry	Good
Oil lubricated	Good
Grease lubricated	Good
Water lubricated	Fair
Process fluid lubricated	Fair

OPERATING PERFORMANCE

Water lubricated	EP22
Process fluid lubricated	EP22

MICROSECTION



POM + Solid Lubricant + Fillers